



# MicroTalc400

## Physical Properties

Brightness	92 %
Specific Gravity	2.68
Moisture	0.10 %
Tapped Bulk Density	0.53
Oil Absorption g/100g	36 ML
D-98	37.0 μ
D-50	08.16 μ
Appearance	Free Flowing Dry Powder
Retention on 400 #	0.10% MAX
Loss on Heating	0.30 % At 105 ± 2° C / 3Hrs
Water Demand Test	80-100 ML / 100 GM

## Particle Size Analysis

