

Talc10M

Physical Properties

Brightness	92 %
Specific Gravity	2.68
Moisture	0.10 %
Tapped Bulk Density	0.39
Oil Absorption g/100g	36 ML
D-98	37.0 μ
D-50	3.46 μ
Appearance	Free Flowing Dry Powder
Retention on 400 #	0.05% MAX
Loss on Heating	0.30 % At 105 \pm 2° C / 3Hrs
Water Demand Test	80-100 ML / 100 GM

Particle Size Analysis

